

Ocean 8 V4.

Technical data.

BERRY  ALLOC

03/2024

	contains	m ²	ft ²	weight
1 pack Ocean 8 V4	9 planks	2,20 m ²	23.71 ft ²	15,7 kg
1 pallet Ocean 8 V4	56 packs	123,34 m ²	1327.61 ft ²	891 kg



product specifications

Dimensions	1288 x 190 mm
Total thickness	8 mm
Bevels	4
Loc System	DuoLoc
Level of use according to European standard EN10874	23 heavy domestic use
	32 general commercial use
Residential warranty	lifetime
Commercial warranty	5 years




Warranty conditions on www.berryalloc.com.

composition

Surface layer	Direct laminated paper, impregnated with melamine resin.
Substrate	Moisture resistant High Density Fiberboard (HDF) treated with hydro+ water repelling technology.
Backing	Direct laminated paper, impregnated with melamine resin.

test results

Abrasion resistance	EN13329	AC4 (IP \geq 4000)
Impact resistance	EN13329	small ball : \geq 35 mm - big ball : \geq 750 mm
Thickness swelling	ISO 24336	12% (requirement \leq 18%)
Water resistance	ISO 4760	up to 24 hours
Fire resistance	EN13501-1	Cfl-S1
Formaldehyde emission	EN717-1	E1
Slip resistance	EN13893	DS
Density	EN323	900 kg/m ³
Resistance to staining	EN438	5 (groups 1+2) ; 4 (group 3)
Effect of a furniture leg	EN16581	no damage (foot type 0)
Effect of a castor chair	EN425	no damage with type W wheels
Thermal resistance in combination with underlay Excellence Plus	ISO 8302	0,08 m ² K/W – Suitable for floor heating/cooling. Detailed instructions on www.berryalloc.com .




laminat.

www.berryalloc.com

03/2024

What is a laminate floor made of?



- ❶ An **overlay** that determines the strength and resistance of your floor
- ❷ A **decor paper** for the design
- ❸ A **high-density fibreboard (HDF)** core
- ❹ A **counterbalance** to stabilise and protect the HDF core
- ❺ The **hydro+** water-repellent coating*

(*) Available for our Ocean+ and Chateau+ collections.