

PRODUKTDATABLAD

The Forest collection



CARPENTER BEE - EK



CARPENTER BEE - BÄNKSIVA

BÄNKSIVA EK FINGERSKARV BC
Benämning: Ekfog BC FS FSC Mix Credit

Produktnamn	Carpenter Bee	Carpenter Bee	Carpenter Bee	Carpenter Bee	Carpenter Bee	Carpenter Bee	Carpenter Bee	Carpenter Bee
Artikelnummer	8973FS17276320	8973FS17276330	8973FS17276336	8973FS17279220	8973FS17279230	8973FS17406320	8973FS17406330	8973FS17406340
EAN	7350088372043	7350088372050	7350088372067	7350088372234	7350088372074	7350088372081	7350088372098	7350088372104
Träslag	Ek	Ek	Ek	Ek	Ek	Ek	Ek	Ek
Kvalite	BC	BC	BC	BC	BC	BC	BC	BC
Konstruktion	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv	Stavlimmad, fingerskarv
Längd (mm)	2020	3020	3620	2020	3020	2020	3020	4000
Bredd (mm)	635	635	635	930	930	635	635	635
Tjocklek (mm)	27	27	27	27	27	40	40	40
Paket- innehåll (m ²)	1.283	1.918	2.299	1.879	2.809	1.283	1.918	2.540
Bruttovikt paket (kg)	23.8	35.5	42.6	34.7	51.9	35.1	52.5	69.5
Nettovikt paket (kg)	23.6	35.2	42.2	34.5	51.6	34.9	52.2	69.1
Rak kant/ Postformad	Postform	Postform	Postform	Postform	Postform	Postform	Postform	Postform
Ytbehandling	Grundoljad	Grundoljad	Grundoljad	Grundoljad	Grundoljad	Grundoljad	Grundoljad	Grundoljad
Certifiering	FSC mixed	FSC mixed	FSC mixed	FSC mixed	FSC mixed	FSC mixed	FSC mixed	FSC mixed
Lim	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581	Akzo 1206+Akzo 2581
Densitet (kg/kbm)	680	680	680	680	680	680	680	680
Fuktutvidgningskoef- ficient (%)	4-10	4-10	4-10	4-10	4-10	4-10	4-10	4-10
Fuktkvot (%)	7-9	7-9	7-9	7-9	7-9	7-9	7-9	7-9
Böjhållfasthet (Mpa)	90-100	90-100	90-100	90-100	90-100	90-100	90-100	90-100
Elasticitetsmodul (Mpa)	10000-13000	10000-13000	10000-13000	10000-13000	10000-13000	10000-13000	10000-13000	10000-13000



NQD
SURFACES